



INDIAN CERAMIC HOUSE

Bone china & Porcelain



Thoughtfully crafted dinnerware features a gilded accent. This dinnerware is perfectly suited for occasional/casual dining.

Brushing products for bone china / porcelain

Product Code	Precious Metal Content	Firing Shade	Type of Body	Remarks
1183	10%, 8%, 7%	Lemon Yellow	Porcelain	Firing Temperature 780c - 840c
674, 681	12%	Yellow	Porcelain & Bone China	Firing Temperature 780 c - 900 c. Pass ASTM Test, Dishwasher resistant. Available in different viscosities.
1148, 1131, 1199, 946	10%	Yellow	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Pass ASTM Test, Dishwasher resistant. Available in different viscosities.
1138, 1179, 1198	8%	Yellow	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Available in different viscosities.
1137, 1178	7%	Reddish - Yellow	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Available in different viscosities.
1152C MW	7%	Darkish Yellow	Bone China & Porcelain	Microwave safe liquid gold. Firing Temperature 780 c - 900 c
MG 682	14%	Yellow	Porcelain	Semi Matt Gold. Firing Temperature 780 c - 860 c. Pass ASTM Test, Dishwasher resistant
Y6418	4%	Rose Gold	Bone China & Porcelain	Firing Temperature 780c - 840c
T6/115	1%	Dark Grey	Bone China & Porcelain	Firing Temperature 780c - 900c.
T6/121	4%	Dark Grey	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Available in different viscosities.
T6/120	10%	Light Grey	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Pass ASTM Test, Dishwasher resistant. Available in different viscosities.
T6/119	12%	Light Grey	Bone China	Firing Temperature 780 c - 900 c.
			& Porcelain	Pass ASTM Test, Dishwasher resistant. Available in different viscosities.
		Amber	Bone China & Porcelain	
		Brown	Bone China & Porcelain	
		Mother of Pearl	Bone China & Porcelain	



Decal products for bone china / porcelain

Product Code	Precious Metal Content	Firing Shade	Type of Body	Remarks
1335	10%	Lemon Yellow	Porcelain	Firing Temperature 780c - 840c. Passes ASTM Test and Dishwasher resistant.
1334	8%	Lemon Yellow	Porcelain	Firing Temperature 780c - 840c
1304X	7%	Lemon Yellow	Porcelain	Firing Temperature 780c - 840c
120	12%	Yellow	Porcelain & Bone China	Firing Temperature 780 c - 900 c. Pass ASTM Test, Dishwasher resistant.
1326B	10%	Yellow	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Pass ASTM Test, Dishwasher resistant.
1319	8%	Yellow	Bone China & Porcelain	Firing Temperature 780 c - 900 c.
SY6461	4%	Rose Gold	Bone China & Porcelain	Firing Temperature 780c - 840c
ST9/88	4%	Light Grey	Porcelain	Firing Temperature 780 c - 900 c. Available in different viscosities.
ST9/179	8%	Light Grey	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Passes ASTM Test and Dishwasher resistant.
ST9/180	12%	Light Grey	Bone China & Porcelain	Firing Temperature 780 c - 900 c. Pass ASTM Test, Dishwasher resistant.
SY64/60	4%	Copper	Porcelain	Firing Temperature 780c - 840c
	-	Amber	Bone China & Porcelain	
	-	Brown	Bone China & Porcelain	
	-	Mother of Pearl	Bone China & Porcelain	

